

CR Coarse Resilient Data Sheet

Subject	Result
Composition	PVC upper and PET base
Type of adhesive	Solvent acrylic
Overall thickness (in)	0.05 in
Tackloop (lb/in)	13.73
Cohesion (minutes/77°F)	2812↑
Peel Adhesion to Stainless Steel (lbf/in – 20 Minute Dwell)	7.03 (AF) FINAT FTMI
Peel Adhesion to Stainless Steel (lbf/in – 24 Hour Dwell)	7.902 (AF) FINAT FTMI
Temperature range	-22°F ~ 176°F
Maximum roll size	54in x 328ft
Life (months)	12 to 24

LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
CR_N (Black)	9004	Black U	0.5	1
CR_Y (Yellow)	1023	108 U	44.5	1
CR_S (Grey)	7046	425 U	5.8	1
CR_T (Clear)	Transparent	Transparent	47.5	12
CR_W (White)	9003	705 U	78.5	1

Coefficient of Friction Data

Test	Dry Surface Test Result	Wet Surface Test Result
ENI6165:2021 Pendulum Test Value (PTV)	0.95	0.6
DIN51130	R10	
NFSI	High traction	

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognized independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

All the above data is for reference only.

©Heskins LLC

