

## GID1616 Photoluminescent Warehouse Marker Data Sheet

Subject	Result	Test Method
Material	Under surface printed OPP	N/A
Type of adhesive	Solvent acrylic (0.0004in)	N/A
Film thickness	0.0016in	N/A
Adhesive thickness	0.0071in	N/A
Total thickness	0.0087in	PSTC-6
Temperature range	-22°F ~ +158°F	See notes below

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

Luminance Test	
Time (minutes)	Luminance (mcd/m <sup>2</sup> )
2	478.4
10	95.1
30	27.7
60	12.17
Decay time (to 0.3mcd/m <sup>2</sup> )	1450 mins

The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS:8493:2008+A1:2010

### LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
H7801 (Green)	6029	3536	55.6	1.4
H7801 (GID)	9010	White	89.9	1.7

All the above data is for reference only.

©Heskins LLC

