

## GRIP Aerated Aluminium Safety-Grip™ Data Sheet

Subject	Result	Test Method
Back carrier	0.005in PVC	Calliper method
Total applied thickness	0.03in	Calliper method
Type of adhesive	Solvent acrylic	N/A
Adhesion to steel (psi)	84↑	PSTC-4
Tensile strength (psi)	336↑	PSTC-3 I
Elongation at break	25%↑	PSTC-3 I
Temperature range	-7.6°F to +316°F	See notes below
Maximum size of production roll	46in x 328ft	N/A

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

### Coefficient of Friction Data

Safety-Grip™	Dry Surface Test Result	Wet Surface Test Result
Standard	102 TRL	71 TRL

Safety-Grip™	Dry Surface Test Result	Wet Surface Test Result	Test Standard
Pendulum	102 TRL	71 TRL	BS EN 13036-4
DIN51130	R13		Certificate UK23247-1817
DIN51097	Inclination 86° - F		97910801.004
NFSI	High traction		Expiry: 12/20/2025

### LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
GRIP_N (Black)	9004	Black U	2.6	1.7

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognized independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

All the above data is for reference only.

©Heskins LLC

