

PHOT2CHV Photo-Luminescent Egress Tape Data Sheet

Subject	Result
Back carrier	0.0059in PVC
Total applied thickness	0.031in
Type of adhesive	Solvent acrylic
Adhesive thickness	0.002in ± 0.0004in
Release paper thickness	0.0067in ± 0.0004in
Adhesion to steel	3.3 lb/in↑
Tensile strength	9 lb/in↑
Elongation at break	25%↑
Temperature range	-23°F to +122°F

Luminance Test	
Time (minutes)	Luminance (mcd/m ²)
2	478.4
10	95.1
30	27.7
60	12.17
Decay time (to 0.3mcd/m ²)	1450 mins

LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
PHTO2CHV (Black/GID)	9017 / 6019	Black / 372 U	0 / 79.5	0 / 5

The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS.8493:2008+A1:2010.

All the above data is for reference only.

©Heskins LLC

